



## FUNCTIONAL PRODUCT GROUP

### NIPPON PAINT SPS ANTIGRAFFITI PRIMER – Anti Graffiti Primer

#### PRODUCT DESCRIPTION

Solvent-based, siloxane-based, transparent, resistant to outdoor weather conditions, anti-graffiti type of surface protection primer material.

#### SPECIFICATIONS

Nippon Paint SPS Antigraffiti Primer has high adherence to the surfaces it is treated with. It is transparent, protects own color of the surface. Does not prevent air permeability of the surfaces thanks to its porous structure.

#### APPLICATION SURFACES

Used for priming before SPS Antigraffiti on all kinds of mineral-based exterior surfaces, concrete, gas concrete, natural stones, absorbent surfaces such as tile and old painted.

#### APPLICATION

Nippon Paint SPS Antigraffiti Primer is ready-to-use. Ensure the application surface is free from oil, dirt, dust and bloated layers, and dry.

A small test is recommended on the surface before application. Apply using a brush, roller or a spray gun. Do not avoid wearing mask while using the spraying method to prevent inhaling its vapor. Avoid applying on surfaces that receives direct sunlight, extreme wind, rain or that is heated by sun. Recommended to be applied in two or three coats for best results on highly absorbent surfaces. Move on to the application of the second coat only after the applied coat is fully absorbed by the surface. Ensure the application surface and ambient temperatures are between +5°C and +30°C. Protect the surface against frost and precipitation for 12 hours before and after application.

Our products should be applied on substructure surfaces that are built in line with General Construction Specifications dated 30.06.2007 and with No. 26568.

#### FOR AIRLESS SPRAYING:

Pressure: 100-121 bars

Nozzle Size (inch): 0.011”

#### THINNING

Ready to use.

#### DRYING TIME

Dries completely in 24 hours under normal ambient conditions.

#### CONSUMPTION

Ranges between 3-6 m<sup>2</sup> per 1 L for single coat depending on surface evenness and absorbency. Controlled sample application must be done for precise coverage / consumption.

#### BETEK BOYA VE KIMYA SANAYI A.Ş.

Zümrütevler Mahallesi Ural Sokak No:38 34852 Maltepe / İSTANBUL

Tel: 0216 571 10 00 Faks: 0216 571 13 15 Mersis No: 0167001238900018 - www.nipponboya.com





### **STORAGE**

May be stored for 1 years in its unopened packaging in a cool environment protected against direct sunlight and frosting.

### **PACKAGE**

0.75 L

This technical sheet is prepared based on laboratory data at normal conditions. Consult technical personnel for details that are not provided hereinabove. Otherwise, the manufacturing company cannot be held responsible for failures that may arise due to lack of knowledge. Our Company reserves the right to change the information provided hereunder.

Where necessary, please refer to Material Safety Data Sheets for more information on health, safety and handling risks, and precautions associated with the products.

**This product is manufactured by Betek A.Ş. with certificate of conformity to the standards TS EN ISO 9001, TS EN ISO 14001, TS 18001, TS EN ISO 50001, TS ISO 10002.**

### **BETEK BOYA VE KIMYA SANAYI A.Ş.**

Zümrütevler Mahallesi Ural Sokak No:38 34852 Maltepe / İSTANBUL

Tel: 0216 571 10 00 Faks: 0216 571 13 15 Mersis No: 0167001238900018 - [www.nipponboya.com](http://www.nipponboya.com)

